REPORT DOCUMENTATION PAGE					OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instruction data needed, and completing and reviewing this collection of information. Send comments reparding this burden estimate or any other expect.					ching existing data sources, gathering and maintaining the	
data needed, and completing and reviewing this collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently						
valid OMB control number. Pl	LEASE DO NOT RETURN YOU	R FORM TO THE ABOVE ADD			,	
1. REPORT DATE (DE		2. REPORT TYPE		 	DATES COVERED (From - To)	
23-03-2007 4. TITLE AND SUBTIT		Final Report			1-10-2004 to 30-11-2006 CONTRACT NUMBER	
Development of a Flow-Through SQUID System					95500510028	
for Non-Destructive Evaluation of MRI Wire				5b.	GRANT NUMBER	
				5c.	PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)					PROJECT NUMBER	
Frederick C. Wellstood						
					TASK NUMBER	
					WORK UNIT NUMBER	
7 DEDECORNING ODGANIZATION NAME(S) AND ADDRESS(ES)					PERFORMING ORGANIZATION REPORT	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Department of Physics					NUMBER	
University of Maryland						
College Park, Maryland,						
20742-4111						
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10.	SPONSOR/MONITOR'S ACRONYM(S)	
AFOSR/PKC (ATTN: Wendy Veon)						
875 North Randolph Street				11	SPONSOR/MONITOR'S REPORT	
Suite 325, Room 3112 Arlington, VA 22203-1768.				'''	NUMBER(S)	
DV (+acro) () 12. DISTRIBUTION / AVAILABILITY STATEMENT					ľ	
DISTRIBUTION STATEMENT A						
Approved for Public Release					FRL-SR-AR-TR-07-0123	
Distribution Unlimited						
Distribution of intriced						
13. SUPPLEMENTARY NOTES						
14. ABSTRACT: This project developed techniques to detect small defects in NbTi magnet wire						
at room-temperature using a flow-through high-transition temperature (T_c) superconducting quantum interference device (SQUID) system. The ability to detect small defects in km-long						
sections of NbTi magnet wire could improve the production yield of high-field magnets for						
power and medical applications. Such magnets are wound from continuous sections of wire up to						
1 km long, and a single small defect in the wire can limit the field the magnet produces,						
making it unsuitable. It is highly desirable to be able to locate defects in wire using non-						
destructive evaluation (NDE) of the wire before the magnet is wound. Ideally, the NDE system						
					retched beyond elastic	
limit) and occlusions (non-conducting impurity grain introduced into the wire). Such defects						
have proven to be difficult to find using visual inspection or conventional eddy current						
detection, and better techniques are needed.						
15. SUBJECT TERMS NDE, Superconducting, SQUID, Magnet						
16. SECURITY CLASSIFICATION OF: 17. LIMI				18. NUMBER	19a. NAME OF RESPONSIBLE PERSON	
10. SECURITY CLASS	DIFICATION OF:		17. LIMITATION OF ABSTRACT	OF PAGES	100. ITALIE OF RESPONSIBLE PERSON	
a. REPORT	b. ABSTRACT	c. THIS PAGE			19b. TELEPHONE NUMBER (include area	
				3	code)	
		1			301-405-7649	

Form Approved

Final Performance Report for

Development of a Flow-Through SQUID System for Non-Destructive Evaluation of MRI Wire

AFOSR Award Number FA95500510028

University of Maryland FRS # 01-5-28399

From: Fred Wellstood

Center for Superconductivity Research

Department of Physics University of Maryland

College Park, Maryland 20742-4111

Phone 301-405-7649, well@squid.umd.edu

To: Air Force Office of Scientific Research

ATTN: Wendy M Veon -PKC 875 North Randolph Street Suite 325, Room 3112 Arlington, VA 22203-1768

Date: March 23, 2007

Cc: Cleopatra White, Center for Superconductivity Research;

Hasti Mehta, Compliance Coordinator,

Office of Research Administration and Advancement, UMD

20070417191

The objective of this project was to develop techniques to detect small defects in km-long sections of NbTi magnet wire at room-temperature using a flow-through high-transition temperature (T_c) superconducting quantum interference device (SQUID) system. The ability to detect small defects in km-long sections of NbTi magnet wire could improve the production yield of high-field magnets for Medical Resonance Imaging (MRI) and power applications. Such magnets are wound from continuous sections of wire up to 1 km long, and a single small defect in the wire can limit the field the magnet produces, making it unsuitable. Ideally, the NDE system must be able to detect small buried defects due to yields (wire stretched beyond elastic limit) and occlusions (non-conducting impurity grain introduced into the wire). Such defects have proven to be difficult to find using visual inspection or conventional eddy current detection, and better technique are needed.

During the two years of this project, the main tasks we accomplished were:

- (1) Built a stepper motor controlled wire feed system and tested it on a cryo-cooled flow-through high-T_c SQUID system;
- (2) Used the system to measure ac magnetic signals from intentional defects (small through holes) in 6 ft long 2 mm diameter brass rod driven at up to 20 cm/s;
- (3) Developed a simple automatic detection scheme using high pass filter and threshold detection to reliably detect through holes down to 300 μm diameter;
- (4) Rebuilt SQUID tip and electronics for higher bandwidth (about 20 kHz) and tested the complete system;
- (5) Developed a simple model of the defect signal, compared observed signals to the model, and developed estimates for minimum defect size observable with a given level of injection current;
- (5) Considered two designs for alternative detection schemes. The aim of the first scheme was to improve the detection of smaller holes by using a coaxial return current path that would produce a field that would cancel the background field from the average current through the wire under test. The aim of the second techniques was to remove the need for making connections to the wire by using a pair of anti-Helmholtz coils to produce a large field gradient that the wire would then be swept through.